

What is claimed is:

1. A process for producing a reactive polyurethane containing free isocyanate groups which comprises reacting a monomeric asymmetrical diisocyanate with a polyhydric alcohol, wherein:
 - 5 (a) diphenylmethane-2,4'-diisocyanate (2,4'-MDI) containing less than 5% 4,4'-MDI and 2,2'-MDI, the 2,2'-MDI content being under 0.4%, is used as the monomeric asymmetrical diisocyanate;
 - (b) at least one diol with a molecular weight of 60 g/mol to 2,000 g/mol is used as the polyhydric alcohol; and
 - 10 (c) the ratio of isocyanate groups to hydroxyl groups is a value of 1.05:1 to 2.0:1.
2. A process as claimed in claim 1, wherein the reactive polyurethane has a Brookfield viscosity at 100°C, as measured by ISO 2555, in the range from 20 mPas to 3,000 mPas.
- 15 3. A process as claimed in claim 1, wherein the content of monomeric asymmetrical diisocyanate in the reactive polyurethane is at most 0.3% by weight.
4. A process as claimed in claim 1, wherein at least one linear or lightly branched C₂₋₁₈ alkanediol is used as the diol.
- 20 5. A process as claimed in claim 1, wherein said reacting is carried out in the presence of at least one catalyst selected from the group consisting of organometallic compounds of tin, lead, iron, titanium, bismuth and zirconium.
6. A process as claimed in claim 1, wherein said reacting is carried out
25 between 30°C and 130°C in the presence of a tin(IV) compound as catalyst.
7. A process as claimed in claim 1, wherein said reacting is carried out at 40 to 75°C.
8. A process as claimed in claim 1, wherein the ratio of isocyanate
30 groups to hydroxyl groups is adjusted to a value of 1.05:1 to 1.5:1.

9. A process as claimed in claim 1, wherein said reacting is carried out between 25°C and 100°C.
10. A process as claimed in claim 1, wherein said at least one diol contains secondary hydroxy groups.
- 5 11. A process as claimed in claim 1, wherein said reacting is carried out in the presence of an aprotic solvent.
12. A process as claimed in claim 1, wherein said reactive polyurethane contains not more than 0.1% by weight asymmetrical diisocyanate.
13. A process as claimed in claim 1, wherein the reactive polyurethane has an NCO content of from 4.5 to 10% NCO.
- 10 14. A process as claimed in claim 1, wherein said at least one diol has a molecular weight of 200 g/mol to 1,500 g/mol.
15. A process as claimed in claim 1, wherein said at least one diol is a polyether.
- 15 16. A process as claimed in claim 1, wherein said at least one diol is selected from the group consisting of reaction products of low molecular weight polyhydric alcohols and alkylene oxides containing 2 to 4 carbon atoms.
17. A process as claimed in claim 1, wherein said at least one diol is polypropylene glycol.
- 20 18. A process as claimed in claim 1, wherein the ratio of isocyanate groups to hydroxyl groups is adjusted to a value of 1.4:1 to 1.9:1.
19. A process as claimed in claim 1, comprising the additional step of reacting the reactive polyurethane with a polyol.
- 25 20. A process as claimed in claim 1, comprising the additional step of reacting the reactive polyurethane with a polyester polyol.
21. A process as claimed in claim 1, comprising the additional step of combining the reactive polyurethane with at least one additional component selected from the group consisting of catalysts, polymeric compounds, stabilizers, adhesion-promoting additives,
- 30

fillers, pigments, plasticizers, and solvents.

22. A process as claimed in claim 1, wherein the monomeric asymmetrical diisocyanate contains at least 97.5% 2,4'-isomers of MDI.
- 5 23. A process as claimed in claim 1, wherein at least one polyol selected from the group consisting of glycerol, trimethylol ethane, trimethylol propane, pentaerythritol, sugar alcohols, and polyether polyols having molecular weights of 100 g/mol to 1,800 g/mol formed by reacting one or more alkylene oxides with glycerol, trimethylol
10 ethane, trimethylol propane, pentaerythritol, sugar alcohols or mixtures thereof is additionally reacted with the monomeric asymmetrical diisocyanate.
24. A process as claimed in claim 1, wherein at least one polyol having a number average molecular weight of 2,000 g/mol to 20,000 g/mol
15 selected from the group consisting of polyesters, polyethers, polyacetals, and polycarbonates is additionally reacted with the monomeric asymmetrical diisocyanate.
25. A reactive polyurethane containing free isocyanate groups obtained by the process of claim 1.
- 20 26. A two component sealant/adhesive comprising at least one reactive polyurethane as claimed in claim 1 and at least one hardener.
27. A moisture-curable sealant/adhesive comprising at least one reactive polyurethane as claimed in claim 1 and at least one aliphatic tertiary amine.

25